

Gallaflo
TimBRE

HIGH QUALITY
ANHYDRITE FLOOR
SCREED FOR **TIMBER**
JOISTED STRUCTURES

TimBRE DATASHEET

DESCRIPTION

Gallaflo TimBRE self compacting flowing screed is made to exacting standards by quality assured manufacturers to BS EN 13813:2002. It is a combination of high quality **Gypsol** binder, specially selected sands, water and special additives where required. It is designed specifically for use in acoustic and non acoustic flooring systems which use timber joists as their primary supporting structure.

Gallaflo TimBRE screed is suitable for the encapsulation of an underfloor heating system, either electric or warm water. **Gallaflo** TimBRE is suited to both residential and commercial properties, and will help to improve the acoustic performance of the floor to meet or exceed Part E of the building regulations. **Gallaflo** TimBRE screed also improves the environmental, fire resistance and durability characteristics and gives a concrete feel to a timber supported floor.

Gallaflo TimBRE screed is designed to be used in conjunction with a compressible or an acoustic resilient insulation and an acoustician should be consulted to approve the design prior to installation where acoustic performance is required. For project specific advice on design and for a model specification, contact our technical and specifications team on 01622 726262.

It is essential that the timber supporting structure is suitably engineered to accommodate the increased loading associated with the screed.



Gypsol is accredited to:



t: 01622 726262
e: quarry@gallagher-group.co.uk
w: www.gallagher-group.co.uk


PHYSICAL DATA

Appearance	Off white fluid mortar
Density	Wet 2200kg/m ³ Dry I 2000kg/m ³
Typical Strength (28 days) kN/m ²	C35-F7
Required Flow (EN13454-2)	230mm to 270mm
Reaction to Fire	Class A1fl non combustible

PERFORMANCE DATA

Working Time :	place and finish within 3 hours of batching
Foot Traffic	24 to 48 hours
Loading	5 to 7 days
Drying (20°C/60% RH)	1 mm per day for first 40mm 0.5mm per day there over
Force Drying	Can be force dried after 7 days

TYPICAL APPLICATION SCHEMATIC



ENVIRONMENTAL DATA

Recycled Content	Binder 98% Mortar up to 40%
Carbon Emissions	Binder 10 to 30kg/tonne Mortar 30 to 50kg/m ³
VOC	Virtually zero
Recyclability	100% ♻️

HEALTH AND SAFETY DATA

Gallaflo TimBRE screeds are delivered to site ready to use via offsite mixing plants, removing the need for labour intensive site mixing and associated mixing equipment.

Gallaflo TimBRE screeds are pumped directly to where they are needed, removing much of the manual handling operations required to install other screeds.

Gallaflo TimBRE screeds are generally pumped using equipment with closed or gridded dispensing hoppers, removing risk of contact with moving machinery.

Gallaflo TimBRE screeds are finished using a lightweight dapping bar requiring no secondary compaction, thus removing most of the physical work needed to lay other screeds. This significantly reduces the negative impact on the musculo-skeletal system of installing contractors. For material safety information please see the relevant health and safety data sheets.